





**Pelle Tan** (WFTA03)

Albury Side Shell, Albury Arm Shell, Albury XL Shell, Bronte Shell, Hugo Shell, Stockholm Shell



Pelle Navy (WFNA03)

Albury Side Shell, Albury Arm Shell, Albury XL Shell, Bronte Shell, Hugo Shell, Stockholm Shell



Pelle Sage (WFSA03)

Albury Side Shell, Albury Arm Shell, Albury XL Shell, Bronte Shell, Hugo Shell, Stockholm Shell



**Pelle Onyx** (WFON03)


Albury Side Shell, Albury Arm Shell, Albury XL Shell, Bronte Shell



Pelle Java (WFJA03)

Albury Side Shell, Albury Arm Shell, Albury XL Shell, Bronte Shell









Warwick Fabrics (Australia) Pty Ltd ABN 56 004 832 455 info@warwick.com.au www.warwick.com.au National Sales Service T 1300 787 888 (toll free in Australia) F +61 (0) 3 9415 7236 F +61 (0) 3 9416 1060 Melbourne 6 - 10 Sackville Street PO Box 1242 Collingwood VIC 3066 T +61 (0) 3 9419 7544

## Pelle

Collection(s)	Contract, Gladiator Iv Book, Pelle, Soumakh
Colour(s)	Bison, Bone, Bordeaux, Donkey, Dove, Fawn, Greenstone, Ivory, Java, Navy, Olive, Onyx, Sage, Sand, Slate, Tan
Product Type(s)	Heavy Commercial
Attributes	Halo Easy Care
Composition	100% Polyester
Pattern Match	No
Pattern Repeat (cm)	Plain
Railroaded	Plain  Fabrics marked Railroaded 'Plain' can be cut in either direction at the discretion of the manufacturer, and in consultation with the customer's preference. Fabric is sampled in the direction it comes up the roll (Non Railroaded).
Width (cm)	140
Roll Size (approx)	35m
Weight (gsm)	360
Origin	Non European
Stain Repellent	No
FIAA Care Label	FIAA Care Label 3 - Non Pile Fabrics
Usage	Upholstery Cushion
Guarantee	3 Years in accordance with our product type and care instructions

## **Test Results**

Wyzenbeek (ASTM D3597, mesh, 4lb/3lb)	100,000 Cycles
Seam Slippage (mm) (ISO 13936-2, Load 180)	Warp 4.8, Weft 4.0
Pilling Resistance (ISO 12945-2)	5
Colourfastness to Light Xenon arc (ISO 105-B02, blue std 6)	5
Colourfastness to Rubbing (ISO 105-X12)	Dry 5, Wet 5
Free and Hydrolysed Formaldehyde (ISO 14184-1:1998)	Not Detectable
Flammability AS/NZS 1530.3 - 1999	
Ignitability (0-20)	9
Spread of Flame (0-10)	0
Heat Involved (0-10)	2
Smoke Developed (0-10)	5





